

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1-22. (Cancelled)

23. (Currently Amended) A coated scrim comprising:

a scrim having a specified air flow resistance; and,

a coating ~~composition~~ applied to ~~said~~ the scrim, the coating comprising filler particles having an average particle size in a range from about 100 microns to about 600 microns in an amount from about 35% to about 90% by dry solids weight;

wherein the coated scrim has ~~an airflow resistance in the range from about 600 mks rays to about 900 and~~ a texture value in a range from about 20 ml/sq ft to about 65 ml/sq ft and a hiding power value of about 98% or greater; and

wherein the change in the value of airflow resistance between the uncoated scrim and the coated scrim is in the range from 240 mks rays to 300 mks rays.

24-25. (Cancelled)

26. (Currently Amended) The coated scrim of claim ~~[[25]]~~ 23, wherein the filler particles are selected from the group consisting of calcium carbonate, dolomite and mixtures thereof.

27. (Currently Amended) The coated scrim of claim [[25]] 23, wherein the coating ~~composition~~ comprises secondary particles selected from the group consisting of ~~vinyl acetate, vinyl propionate, vinyl butyrate, ethylene, vinyl chloride, vinylidene chloride, vinyl fluoride, vinylidene fluoride, ethyl acrylate, methyl acrylate, propyl acrylate, butyl acrylate, ethyl methacrylate, methyl methacrylate, butyl methacrylate, hydroxyethyl methacrylate, styrene, butadiene, urethane, epoxy, melamine, ester~~ titanium dioxide, barium sulfate, clay, mica, calcium carbonate, limestone, dolomite, silica, talc, perlite, gypsum, wollastonite, calcite, aluminum trihydrate, zinc oxide, zinc sulfate, polymers, pigments and combinations thereof.

28. (Currently Amended) The ~~coating~~ coated scrim of claim 27, wherein the secondary particles have an average particle size in the range from about 0.1 to about 30 microns.

29. (Currently Amended) The coated scrim of claim 27, wherein the coating ~~composition~~ contains the secondary particles in an amount from about 5% to about 55% by weight on a dry solids basis.

30. (Currently Amended) The coated scrim of claim [[25]] 23, wherein the coating ~~composition~~ further comprises a polymeric binder formed of a monomer selected from the group consisting of vinyl acetate, vinyl propionate, vinyl butyrate, ethylene, vinyl chloride, vinylidene chloride, vinyl fluoride, vinylidene fluoride, ethyl acrylate, methyl acrylate, propyl acrylate, butyl acrylate, ethyl methacrylate, methyl methacrylate,

butyl methacrylate, hydroxyethyl methacrylate, styrene, butadiene, urethane, epoxy, melamine, ester and combinations thereof.

31. (Currently Amended) The coated scrim of claim 30, wherein the coating ~~composition~~ further comprises a pigment, the coating composition having a pigment to binder ratio in a range from about 5:1 to about 30:1 on a dry solids basis.

32. (Currently Amended) The coated scrim of claim ~~[[25]]~~ 23, wherein the filler particles have an average particle size in a range from about 200 to about 450 microns.

33. (Currently Amended) The coated scrim of claim 23, wherein the coating ~~composition~~ has a solids content in a range from about 50% to about 85% by weight.

34-52. (Cancelled)

53. (New) The coated scrim of claim 23, wherein the scrim is a fiberglass scrim.

54. (New) The coated scrim of claim 53, wherein the fiberglass scrim is a facing for a flat panel sound radiator.